

Aliphatic Hydrocarbon Resins

Hot Melt Adhesive(HMA) /
HMPSA / Tapes /
Hot Melt Road Marking(HMRM) /
Tire



Specifications

3) 100% Molten Resin 4) 100% Molten Resin (200°C, 3hrs / H-Series : 200°C, 5hrs)

Item Unit	Softening Point°C	Color ³⁾ Gardner#	Heat Stability ⁴⁾ Gardner#	Acid Value KOHmg/g	Melt Viscosity at 200°C, cps	Features	Production Site
Test Method	ASTM E 28	ASTM D 1544	ASTM D 1544	ASTM D 1639	ASTM D 3236		
A-1100	94 ~ 102	Max. 6	Max. 8	Max. 1	Max. 200	General Purpose	Ulsan
A-1100S	94 ~ 102	Max. 6	Max. 8	1.00 ~ 1.99	Max. 200	Acid Modified Resin	Ulsan
A-1115	108 ~ 116	Max. 6	Max. 8	Max. 1	-	High SP	Ulsan
A-2115	108 ~ 116	Max. 6	Max. 8	Max. 1	-	High SP, Low Molecular Weight	Ulsan
C-1100	94 ~ 102	Max. 6	Max. 8	Max. 1	-	High Molecular Weight	Ulsan
R-1095	93 ~ 99	Max. 6	Max. 8	2.00 ~ 3.00	-	Acid Modified Resin	Ulsan
R-1100S	94 ~ 102	Max. 6	Max. 8	2.00 ~ 3.00	Max. 250	Acid Modified Resin	Ulsan
T-1080	80 ~ 90	Max. 6	Max. 8	Max. 1	-	C9 Modified Resin	Ulsan
T-1095	84 ~ 98	Max. 6	Max. 8	Max. 1	-	C9 Modified Resin	Ulsan
T-1100	94 ~ 102	Max. 6	Max. 8	Max. 1	-	C9 Modified Resin	Ulsan
T-3100	94 ~ 102	Max. 8	Max. 10	Max. 1	-	Highly C9 Modified	Ulsan
H-2100	97 ~ 106	Max. 3	Max. 8	Max. 0.1	-	Hydrogenated, Good Heat Stability	Yeosu, Daesan
H-2200	95 ~ 105	Max. 4	Max. 8	Max. 0.1	-	Hydrogenated, Highly C9 Modified	Yeosu, Daesan
H-2300	95 ~ 105	Max. 3	Max. 8	Max. 0.1	-	Hydrogenated, C9 Modified Resin	Yeosu, Daesan

Applications

Application	Main Components	Recommended HIKOREZ® Grades
Tapes	NR, SIS, SBR	A-1100(S), A-1115, A-2115, C-1100, T-1080, T-1095, T-1100, T-3100, H-2100, H-2300
Pressure Sensitive Adhesives	NR, BR, SIS	A-1100(S), A-1115, A-2115, H-2100, H-2200, H-2300
Hot Melt Adhesives	EVA	A-1100(S), A-1115, A-2115, C-1100, T-1080, T-1095, T-1100, T-3100, H-2100, H-2300
Solvent Based Adhesives	CR, SBR	C-1100, H-2200, H-2300
Hot Melt Road Marking	Fillers	A-1100S, R-1095, R-1100S
Rubber Compounding	NR, BR, SBR	A-1100, C-1100, T-1095, T-3100
Asphalt Modification	Asphalts	A-1115, R-1100S
Wax Compounding	Wax	A-1100, C-1100, H-2100
Sealants	LDPE, APO	A-1100, C-1100, H-2100



KOLON INDUSTRIES, INC.

MAIN OFFICE, PLANTS AND RESEARCH CENTER

Main Office

4th FL., Kolon One&Only Tower office building, 110, Magokdong-ro, Gangseo-gu, Seoul, Republic of Korea
Tel : +82-2-3677-6105/6133 Fax : +82-2-6280-6192

KOLON Central Research Park

5th FL., Kolon One&Only Tower R&D building, 110, Magokdong-ro, Gangseo-gu, Seoul, Republic of Korea
Tel : +82-2-580-0918 Fax : +82-2-576-3963

Ulsan Plant

33, Sapyeong-Ro, Nam-gu, Ulsan, Republic of Korea
Tel : +82-52-259-8130 Fax : +82-52-260-1192

Yeosu Plant

213, Sandanjungang-ro, Yeosu-si, Jeollanam-do, Korea
Tel : +82-61-690-9860 Fax : +82-61-690-9882

Daesan Plant

100, Daejuk 1-ro, Daesan-eup, Seosan-si, Chungcheongnam-do, Korea
Tel : +82-41-661-5740 Fax : +82-41-661-5759

OVERSEAS SUBSIDIARIES

KOLON EU GmbH

Arabella Center 7A Lyoner str. 44-48, 60528 Frankfurt/Main, Germany
Tel : +49-(0)69-9622-1540 Fax : +49-(0)69-9622-1515

KOLON USA, Inc.

115 Perimeter Center Place, Suite 815, South Terraces, Atlanta, Georgia 30346 USA
Tel : +1-770-609-6194 Fax : +1-770-609-6198

KOLON (Suzhou) Company Limited

Qingqiuji 56, Suzhou Industrial Park, Suzhou, Jiangsu province, 215126 China
Tel : +86 186 6229 6494

KOLON WEBSITES

KOLON Industries Website

www.kolonindustries.com

KOLON HCR Website

www.kolonhcr.com
www.hikorez.com

www.sukorez.com
www.hikotack.com




K·Resinas

Comércio e Importação de Resinas

Tel./Fax: +55 11 3081-9656
Al. Lorena, 1304 - cj. 1302/1303
01424-001, São Paulo, SP, Brasil